



**CITADEL®  
FORTIFICATION FORMULA KIT SLOW**

**DESCRIPTION AND USES**

Citadel® Fortification Formula Kit Slow is a two component, 100% solids polyurea crack repair compound. This ultra-fast cure crack repair can be used at temperatures as low as -5°F (-20.5°C) and is suitable for traffic in 30 minutes.

**PRODUCT FEATURES**

- Bonds well to a variety of substrates including concrete, wood, fiberglass and asphalt
- Fast cure times, even in cold temperatures
- Return to service in 30-60 minutes
- Virtually no odor

**PRODUCT**

SKU	DESCRIPTION (Kit)
390098	Gray

**PACKAGING**

1 gallon kit containing both components Part A and Part B components are packaged in 1/2-gallon plastic containers. Kit yields one full gallon.

**PRODUCT APPLICATION**

**READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT**

**SURFACE PREPARATION**

New concrete must cure 30 days at 70°F (21°C) before repairs are made. Remove all dirt, grease, oil, salt, or other contaminants by washing surface with Krud Kutter® PRO Cleaner Degreaser, commercial detergent or other suitable cleaner. Rinse thoroughly with fresh, clean water. Remove all loose, unsound, or deteriorated concrete.

Small hairline cracks must be chased using a V-shaped diamond crack chasing blade on a handheld grinder. The crack should be opened to a minimum of ¼ inch wide. Any oil or grease that may have seeped into a crack and contaminated the edge of the concrete must be removed by grinding if washing is not sufficient. Use dry silica sand to fill deep cracks leaving a depth of ¼ inch down from the surface. The Fortification Formula Kit Slow will soak into the silica and fortify the patch.

**PRODUCT APPLICATION (cont.)**

**MIXING**

Mix both components separately prior to combining. Pour out equal volumes of each component, then combine and mix together for 20-30 seconds Fortification Formula Kit Slow cures very quickly, so only mix up amounts that can be used within 10 minutes. Once mixed, Fortification Formula Kit Slow is an easy flowing liquid. For some repairs, such as spalled areas or edge repair, dry silica sand can be added and mixed in to create a trowelable paste. Never use more than one part silica to one part activated liquid.

**APPLICATION**

Fortification Formula Kit Slow is suitable for application temperature down to -5°F (-20.5°C). Within one minute of mixing, pour Fortification Formula Kit Slow into the crack to be filled. Fill the crack to a slight excess and allow to cure. Fortification Formula Kit Slow will cure in 15-30 minutes. Once cured, and the material cannot be indented by a thumbnail, the excess material can be removed by grinding to a flush surface.

**NOTE:** Fortification Formula Kit Slow must be profiled by grinding or sanding if it is going to be topcoated.

**THINNING**

None required.

**CLEAN-UP**

Methyl Ethyl Ketone (MEK).

**PERFORMANCE CHARACTERISTICS**

**TENSILE STRENGTH**

METHOD: ASTM D412  
RESULT: 4,800

**ABRASION RESISTANCE**

METHOD: ASTM D4060, CS 17 Wheel, 1,000 g load, 1,000 cycles  
RESULT: 20 mg loss

**HARDNESS, DUROMETER**

METHOD: ASTM D2240  
RESULT: 67-72 D

**COMPRESSIVE STRENGTH**

METHOD: ASTM C109  
RESULT: 5,600 and with silica added 6,200

**ELONGATION**

METHOD: ASTM D412  
RESULT: 6-8%

	<b>TECHNICAL DATA</b>	<b>CDL-20</b>
	<b>CITADEL®</b> <b>FORTIFICATION FORMULA KIT SLOW</b>	

**PHYSICAL PROPERTIES**

		FORTIFICATION FORMULA KIT SLOW
<b>Resin Type</b>		Polyurea
<b>Solids</b>	<b>By Weight</b>	100%
	<b>By Volume</b>	100%
<b>Mixing Ratio</b>		1 (base):1 (activator) by volume
<b>Induction Period</b>		None
<b>Working Time</b>		5-8 minutes @ 77°F (25°C)
<b>Pot Life</b>		None. Pour out all material immediately after mixing
<b>Estimated Coverage*</b>		230 linear feet per activated gallon @ 1/4" wide and 1/4" deep
<b>Dry Times at 72°F (22°C) and 50% Relative Humidity</b>	<b>Dry Hard</b>	20-30 minutes
	<b>Foot Traffic</b>	30 minutes
	<b>Vehicle Traffic</b>	60 minutes
<b>Shelf Life</b>		2 years
<b>Safety Information</b>		See SDS

\*Coverage rate is estimated and accounts for material lost when grinding away excess material for a smooth finish.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.